# TRUEPREP SURFACE CLEAN

**TDS99-520**

| | |
|---|---|
| **DESCRIPTION** | TRUEPREP SURFACE CLEAN is a powerful water based, biodegradable, degreaser. Formulated to remove grease and other contaminants from painted and other surfaces to enable over coating where a high degree of surface preparation is not possible, especially on industrial paints such as 2 pack epoxies, and 2 pack urethanes. It can be used for restoration of aged painted surfaces, or general cleaning and degreasing prior to paint preparation. |
| **TYPICAL USES** | All exterior surfaces. Including pre preparation cleaning of Swimming pools and Flooring. |
| **ENVIRONMENT** | Exterior cleaning. Also ideal for cleaning interior surfaces (Flooring, Kitchens, commercial environments) that are heavily contaminated and can be rinsed clean without affecting adjacent surfaces. |
| **PERFORMANCE** | Effectively removes fats and degreases surfaces. Also effectively removes alkali and mineral salt deposits, often on swimming pool surfaces, that solvent washing may not remove. |
| **LIMITATIONS** | DO NOT allow to dry on to the surface or a whitish residue will be left on the surface and re-application of TRUEPREP SURFACE CLEAN will be necessary to remove this residue. |
| **TECHNICAL DATA** | Product Type: Solution of Surfactants<br>Solvent: Water<br>Appearance: Opaque<br>Primer: Not applicable<br>Durability: Good<br>Thining and Clean Up: Water<br>Pack Size: 99-520.05, 20<br>VOC: 0<br>Vol Solids: 0 percent<br>Touch Dry: 15 minutes @20°C<br>Recoat Time: 1 Hour @20°C<br>Number of Coats: Varies with specification.<br>Theoretical Coverage: 7 $m^2$/litre/coat<br>Wet Film Thickness: 0 microns<br>Dry Film Thickness: 0 microns |
| **SPREAD RATE** | 5-10 - $m^2$/litre/coat<br>Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness. |
| **PRODUCT CODES** | 99-520.05<br>99-520.20 |
| **SURFACE PREPARATION** | **Cementitious-CLEANING General**<br>Waterblast, broom or blow down surfaces to remove visible surface contamination and excessive surface debris. Allow to dry.<br><br>Mix TRUEPREP SURFACE CLEANER to desired concentration level. Apply by backpack sprayer or watering can working in sections, scrubbing to agitate the product on the surface to be painted. Leave for up to 15 minutes, not allowing the product to on the surface dry. Rinse clean, with power wash (min 3500 psi) or high-volume low-pressure water to remove all residue and any loose material.<br><br>Check the surface is totally clean, and if necessary, repeat and if required adjust concentration level. All surfaces must be clean, and free from dirt, grease, and any other surface contaminant prior to surface preparation and painting.<br><br>Moss and Algae: Any algae growth on surfaces must be killed off. The pool will need to be emptied and then treated with TRUEPREP GREEN-KILL following the manufacturer's instructions. This could take multiple applications. Failure to do this and completely kill the roots of the algae that will have grown into the substrate could lead to paint failure and re growth in those areas. |

**Fibreglass-CLEANING General**
If painting a pool, before starting the job refer to Cotec Information sheet: PS-C011 Fibreglass Pools Hydrostatic Pressure and Emptying MAR 21

Waterblast, broom or blow down surfaces to remove visible surface contamination and excessive surface debris. Allow to dry.

Mix TRUEPREP SURFACE CLEANER to desired concentration level. Apply by backpack sprayer or watering can working in sections, scrubbing to agitate the product on the surface to be painted. Leave for up to 15 minutes, not allowing the product to on the surface dry. Rinse clean, with power wash (min 3500 psi) or high-volume low-pressure water to remove all residue and any loose material.

Check the surface is totally clean, and if necessary, repeat and if required adjust concentration level. All surfaces must be clean, and free from dirt, grease, and any other surface contaminant prior to surface preparation and painting.

Moss and Algae: Any algae growth on surfaces must be killed off. The pool will need to be emptied and then treated with TRUEPREP GREEN-KILL following the manufacturer's instructions. This could take multiple applications. Failure to do this and completely kill the roots of the algae that will have grown into the substrate could lead to paint failure and re growth in those areas.

## MIXING INSTRUCTIONS

Can be used neat, or diluted 1:10 with water. Test dilution rate on an inconspicuous area, prior to bulk mixing to ensure efficient and effective use.

## APPLICATION

Pump spray pot or backpack sprayer, broom or brush. Leave to dwell and scrub for up to 15 minutes.

Scrubbing with a DECK SCRUB will assist in removing difficult to remove residue and contamination.
Rinse, or water blasted off with water.

**SPRAY**
Backpack sprayer. DO NOT atomise to a fine mist.

**BRUSH/ROLLER**
Broom

**CLEAN UP**
Water

## THINNING

Water

## SAFETY PRECAUTIONS

Refer to the Safety Data Sheet for this product prior to use. Please ensure that they are familiar with all aspects concerning safe application of this product, including appropriate personal protective equipment (PPE). If you are unsure about any health and safety aspects of this product, do not use it.

## ENVIRONMENTAL

This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET

**COATING TECHNOLOGIES LIMITED**
**10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz**

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.