EPOTEC SL HARDENER

TDS60-1000

DESCRIPTION	A two-pack epoxy hardener for use with Epotec SL Self Levelling swimming pool floor paint.
ENVIRONMENT	Imersion
LIMITATIONS	Not suitable for use as a tank lining for vegetable oils and fatty acids such as lactic or acetic acid. Product has strong exotherm. Not recommended as a coating for polyethylene or acrylic swimming pools. Do NOT apply EPOTEC SL EPOXY when the air temperature is below 15 and no application at all should be attempted below 13 ground temperature particularly in wet or humid conditions.
TECHNICAL DATA	Resin: Epoxy/Polyamine Appearance: Clear Thining and Clean Up: Epotec 107 Thinner Pack Size: 4 Mixing Ratio: 4:1 Vol Solids: 100 percent Touch Dry: 5-7 hours @20°C Recoat Time: Overnight @20°C Theoretical Coverage: 4 m^2/Kg/coat Wet Film Thickness: 190 microns Dry Film Thickness: 190 microns
SPREAD RATE	First Coat: 4 - m^2/Kg/coat Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness.
PRODUCT CODES	61-1000
ENVIRONMENTAL	This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET