# PROSPEC LE WB ENAMEL LOW SHEEN

**TDS01-755**

| | |
|---|---|
| **DESCRIPTION** | High quality interior water-based enamel coating. |
| **TYPICAL USES** | Interior surfaces including wall boards, plywood. Ideally suited to high contact and wet service areas such as hallways, kitchens, bathrooms for both walls and ceilings where a washable surface is required. |
| **PERFORMANCE** | Designed to be used in place of alkyd (Oil) based paints, to provide durable, hard wearing surfaces. Good burnish and stain resistance. Non yellowing |
| **LIMITATIONS** | Do not apply if the air and surface temperature during application is likely to fall below 10°C. |
| **TECHNICAL DATA** | Solvent: Water<br>Appearance: White<br>Colour: White and Pastel<br>Primer: See over.<br>Durability: Excellent<br>Thining and Clean Up: Water<br>VOC: <55g/litre<br>Vol Solids: 32 percent<br>Touch Dry: 30 minutes @15°C<br>Recoat Time: 2-4 Hours @20°C<br>Number of Coats: 2<br>Theoretical Coverage: 10 m²/litre/coat<br>Wet Film Thickness: 100 microns<br>Dry Film Thickness: 32 microns |
| **SPREAD RATE** | 10-12 - m²/litre/coat<br>Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness. |
| **PRODUCT CODES** | 01-755.04 |
| **SURFACE PREPARATION** | **Timber - dressed-New Unpainted STAINING**<br>All surface contaminants must be removed leaving the surface clean of dirt, grease and any other form of contamination. Ensure the timber is dry and has a moisture content of less than 15% before application.<br><br>Inspect the substrate prior to applying any coating system to ensure there is no surface defects.<br><br>DEFECTS: Repair or fill as required, taking care to use a filler of similar tone to the timber, prior to applying first coat.<br><br>Sand all surfaces to be painted to an even flat smooth finish to provide a good key for the new paint system. Dust down and wipe with a damp cloth to remove all dust. Allow to dry.<br><br>**Timber-New Unpainted PAINTING**<br>All surface contaminants must be removed leaving the surface clean of dirt, grease and any other form of contamination. Ensure the timber is dry and has a moisture content of less than 15% before application.<br><br>Inspect the substrate prior to applying any coating system to ensure there is no surface defects that require repair prior to applying first coat.<br><br>Sand all surfaces to be painted to an even flat smooth finish to provide a good key for the new paint system. Dust down and wipe with a damp cloth to remove all dust. Allow to dry.<br><br>DEFECTS: If required, apply appropriate flexible paintable sealant, to gaps between skirting boards, framing and scotia's and fill any minor defects using TRUEPREP STOP-IT Filler, after primer coat is dry. |
| **APPLICATION** | Brush or roller (Wooster Pro-dooz 10-13mm nap dacron roller and premium brush). Add up to 5% Cotec Summer Retarder on hot, windy days to reduce drag and keep a wet edge.<br>Airless spray application: Pressure 2500-full pressure psi, max. tip size 413. 100 Mesh Gun Filter |

| | |
|---|---|
| **THINNING** | Water |
| **ENVIRONMENTAL** | This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET |

**COATING TECHNOLOGIES LIMITED**
**10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz**

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.