PROSPEC MF MIRROR FINISH WB ENAMEL

TDS01-340

DESCRIPTION	A low odour industry first, high build waterbased Enamel finish coat that when applied over Prospec Holdout Sealer delivers a finish that is traditionally only achieved with Lacquer or Oil based enamels. Prospec Mirror Finish Enamel is based on a novel polymer platform that conveys excellent early toughness and chemical resistance to the coating's properties.
TYPICAL USES	Exterior/interior surfaces including skirtings, window frames, doors, and residential cabinetry.
PERFORMANCE	Provides a durable, hard wearing surface where a Premium Door and Trim finish is required. Cleanable surface using detergent and moist microfibre cloth. Prospec Mirror Finish shows excellent blocking resistance and chemical resistance and is non-yellowing.
LIMITATIONS	Do not apply if the air and surface temperature during application is likely to fall below 10°C. Interior: Spraying below 15°C. post spray heating is required. Above 15°C use air-fans to assist airflow and accelerate drying. Designed for spray application and can be touched up with microfibre roller or brush.
TECHNICAL DATA	Resin: Acrylic Solvent: Water Appearance: White Colour: White and Pastel Primer: See over. Durability: Excellent Thining and Clean Up: Water VOC: <55g/litre Vol Solids: 32 percent Touch Dry: 2 hours @15°C RH <70% Recoat Time: 2-4 Hours @20°C Number of Coats: 2 Theoretical Coverage: 6 m²/litre/coat Wet Film Thickness: 160 microns Dry Film Thickness: 51 microns
SPREAD RATE	6-8 - m²/litre/coat Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness.
PRODUCT CODES	01-340.04
SURFACE PREPARATION	**Timber - dressed-New Unpainted STAINING** All surface contaminants must be removed leaving the surface clean of dirt, grease and any other form of contamination. Ensure the timber is dry and has a moisture content of less than 15% before application. Inspect the substrate prior to applying any coating system to ensure there is no surface defects. DEFECTS: Repair or fill as required, taking care to use a filler of similar tone to the timber, prior to applying first coat. Sand all surfaces to be painted to an even flat smooth finish to provide a good key for the new paint system. Dust down and wipe with a damp cloth to remove all dust. Allow to dry.

Timber-New Unpainted PAINTING
All surface contaminants must be removed leaving the surface clean of dirt, grease and any other form of contamination. Ensure the timber is dry and has a moisture content of less than 15% before application.

Inspect the substrate prior to applying any coating system to ensure there is no surface defects that require repair prior to applying first coat.

Sand all surfaces to be painted to an even flat smooth finish to provide a good key for the new paint system. Dust down and wipe with a damp cloth to remove all dust. Allow to dry.

DEFECTS: If required, apply appropriate flexible paintable sealant, to gaps between skirting boards, framing and scotia's and fill any minor defects using TRUEPREP STOP-IT Filler, after primer coat is dry.

APPLICATION	Spray: Airless unit Graco 395 or larger. Pressure 2,500-2,700psi max and a 308 tip with 100 mesh filter at gun.
THINNING	Clean up in water. Use a small amount of detergent to aid clean up.
ENVIRONMENTAL	This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET

COATING TECHNOLOGIES LIMITED
10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.