



High Performance Paint Product Data Sheet



TUFF COTE 2K EPOXY

49-130X AUG 14



DESCRIPTION: Environmentally friendly high-build 2-pack water based anti-corrosive epoxy for direct to metal applications.

TYPICAL USES: Excellent adhesion to well prepared substrates. Specially designed to protect metallic surfaces. The applications include truck chassis, trailers, beams, poles, roofs, fences and other light to medium industrial steel structures. For other surfaces, such as concrete, wood and plastic, please use alternative products such as EPOTEC HIGH BUILD EPOXY or TUFF FLOOR WB EPOXY. Does not require a topcoat in interior or unexposed environments.

PERFORMANCE: This is a premium epoxy coating with superior adhesion to ferrous and non-ferrous metals. Abrasion resistance, flash-rust resistance, chemical resistance and anti-corrosive properties. Easy to apply. Water clean up.

LIMITATIONS: Do not apply where temperatures are below 10°C. Always ensure the product has covered all of the substrate, re-coat or touch-up if necessary, before topcoats are applied. Epoxies could take several hours to reach initial hardness, avoid rain or water splashing onto the uncured surfaces. Mix product well before use as heavy anti-corrosive pigments can settle.

TECHNICAL DATA:

Resin:	Two component epoxy
Solvent:	Water
Finish:	Low Sheen (5-8% @ 60°)
Colour:	Grey
Touch Dry (minimum):	6 hours @ 20°C
Recoat Time (minimum):	Overnight
Primer:	Not Required
Number of Coats:	2
Dry Film Thickness:	50-62 microns at 10-8 m ² /kg
Wet Film Thickness:	100-125 microns at 10-8 m ² /kg
Durability:	Very good
Thinning and Clean Up:	Water
VOC:	43 g/litre
Pot Life:	60-90 minutes @20°C
Mixing Ratio:	5:1 by weight
Pack Size:	3, 9 Kg

SPREAD RATE:

Theoretical Coverage: 8-10 m²/kg/coat.
Coverage depends on surface profile and porosity.

COMPUTER CODES:

Tuff Cote 2K Epoxy White 49-1301

Coating Technologies Limited, 16 Aetna Place, Henderson, Auckland, New Zealand

Phone: 0064 9 837 0897 Fax: 0064 9 837 3736 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.

TUFF COTE 2K EPOXY

SURFACE PREPARATION:

(Refer to "Surface Preparation and Paint Systems" for full details). To ensure a successful application all surfaces to be coated must be clean, dry and stable.

Note: Commencement of work on a surface means in general you accept that surface. If any doubt about condition etc, seek advice.

TUFF COTE 2K EPOXY can be used as a topcoat in interior or unexposed applications. 2 – 3 coats of TUFF COTE 2K EPOXY are recommended to achieve desired protection against corrosion, abrasion and chemicals.

STEEL/IRON:

Remove all rust, grease and oil. Apply 1 coat TUFF COTE 2K EPOXY, after overnight cure at 20°C; recoat with TUFF COTE 2K EPOXY, or for a decorative finish, apply 2 coats of AQUATEC LP or TUFF COTE FINISH.

ALUMINIUM/BRONZE:

Remove all rust, grease and oil. Apply 1 coat TUFF COTE 2K EPOXY, after overnight cure at 20°C; for a decorative finish, apply 2 coats of AQUATEC LP or TUFF COTE FINISH.

GALVANISED IRON:

Galvanised iron sheets that are lapped must be coated in the lap areas to stop corrosion.

NEW: All new galvanised iron has an oil/grease coating from roll forming and it must be removed before coating. This can be done by leaving the roof exposed to the elements for 3 months before painting or by using a suitable roof wash solution.

OLD: Wash all areas with a suitable roof wash solution. Areas of rust must be wire-brushed, to remove loose rust etc. Apply RUST KILL to convert any remaining rust. Wash area thoroughly and allow to dry.

Apply 1 coat TUFF COTE 2K EPOXY. After overnight cure at 20°C; apply 2 coats of ACRYLIC ROOF PAINT or AQUATEC LP.

If roofs are being used for collection of drinking water, it is strongly recommended that roof down pipes are disconnected until after the first major rainfall event ($\geq 10\text{mm}$).

NON-METALLIC SURFACES:

For surfaces such as concrete, wood or plastic, please use alternative water based epoxy products, such as TUFF FLOOR WB EPOXY or EPOTEC HIGH BUILD EPOXY.

APPLICATION:

Mix Part A well, ensuring the product is free-flowing before adding Part B. Mix Part B into Part A with a broad paddle for 2-3 minutes, ensuring that sides and bottom of the pot have been completely mixed in.

BRUSH AND ROLLER: Use product as is or add 5-10% water. This will ease roller/ brush drag and assist in keeping a wet edge.

ROLLER: Use an 8-12mm nap dacron roller.

SPRAY: Airless spraying is recommended. Pressure 2,500psi max and 413 tip for general application. Add 5-10% water if necessary. Airless spray will deliver a higher film build, about 275 microns per coat. Best performance is achieved by an initial low-build pass (tack coat), followed by a full spray of finish coat.

End of pot-life is observed when stirring does not return the product to a free flowing state. Prior to re-coating, test the coating by pressing your thumb into the coating for 2 seconds. Re-coat only if no impression is made in the coating. Generally overnight cure is required.

THINNING & CLEAN UP:

Only thin after parts A and B have been thoroughly mixed. Addition of water before thorough mixing of Part A with Part B will result in poor performance of product. Clean up with water and detergent.

ENVIRONMENTAL:

This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET.